BRONZE ALLOYS

Here are some of the alloys of normal production. Beside the international matches.
It 'also possible the realization of bronze alloys other than those listed in the table. Please contact the sales office indicating the type of alloy and the amount requested by you.

Click on the symbol to display the page with the tab on the mechanical properties of the alloy.

Lega	UNI	EN 1982	DIN	ASTM	SAE	BS	AFNOR
Italia	EU		GER	USA			
CuSn12	7013/72-2^		CC483K	G-SnBz12			-

DIN 1705	U-E 12P			
CuSn11Pb2	-	CC482K	CuSn12Pb	-

DIN 1705	CuSn12			
CuSn12Ni2	-	CC484K	CuSn12Ni	-

DIN 1705				
CuSn10	7013/72-1^	CC480K	G-SnBz10	-

DIN 1705	U-E 10P		
CuSn5Zn5Pb5	7013/72-8^	CC491K	G-RG5

				B 145 4A
DIN1705	CuPb5Sn5Zn5			
CuSn7Zn4Pb7	7013/72-7^	CC493K	G-RG7	
				B 144 3B
DIN1705	CuSn7Pb6Zn4			
CuSn10Pb10	7013/72-3^	CC495K	G-SnPbBz10	B 144 3A
DIN 1716	CuPb10Sn10			
CuSn7Pb15	7013/72-4^	CC496K	G-SnPbBz15	B 144 3D-

DIN 1716		U-Pb 15 E8				
CuAl11Fe4Ni4	5275	CC333G	CuAl10Fe5Ni5	B 148 9D-955	701 C	
DIN 1714		UA 10 N				
CuAl11Fe4	5274	CC331G	FeAlBzF50	B 148 9C-954		
DIN 1714						
CuAl9Fe	5273	CC330G	CuAl9Fe3	B 148 9A-952		68
DIN 1714		UA 9 N Fe				

N.B. I dati presenti in tabella sono indicativi in quanto non esiste una precisa equivalenza tra le norme.